

# Superparamagnetic-Like Behaviour in RE<sub>2</sub>WO<sub>6</sub> Tungstates (Where RE = Nd, Sm, Eu, Gd, Dy, Ho and Er)

T. GROŃ<sup>a</sup>, E. TOMASZEWICZ<sup>b</sup>, P. URBANOWICZ<sup>a</sup>, H. DUDA<sup>a</sup> AND T. MYDLARZ<sup>c</sup>

<sup>a</sup>Institute of Physics, University of Silesia, Uniwersytecka 4, 40-007 Katowice, Poland

<sup>b</sup>Department of Inorganic and Analytical Chemistry, West Pomeranian University of Technology  
al. Piastów 42, 71-065 Szczecin, Poland

<sup>c</sup>International Laboratory of High Magnetic Fields and Low Temperatures, Gajowicka 95, 53-529 Wrocław, Poland

The magnetization isotherms were used to study the superparamagnetic-like behaviour in polycrystalline (powder) RE<sub>2</sub>WO<sub>6</sub> tungstates (where RE = Nd, Sm, Eu, Gd, Dy, Ho and Er). The magnetization isotherms of the majority tungstates under study revealed both the spontaneous magnetic moments and hysteresis characteristic for the superparamagnetic-like behaviour with blocking temperature  $T_B \approx 30$  K except the Sm<sub>2</sub>WO<sub>6</sub> and Eu<sub>2</sub>WO<sub>6</sub> compounds.

PACS: 75.20.-g, 75.25.Dk, 75.30.Cr, 73.61.Ng

## 1. Introduction

The magnetic and electrical measurements carried out on the RE<sub>2</sub>WO<sub>6</sub> (where RE = Nd, Sm, Eu, Gd, Dy and Ho) tungstates showed a paramagnetic behaviour for samples with RE = Nd, Gd, Dy and Ho and more complex ones for samples with RE = Sm and Eu in the temperature range 4.2–280 K and an insulating state at room temperature [1]. A fitting procedure of the Curie–Weiss law, eliminating the temperature independent contribution from the experimental susceptibility data, showed a negative contribution (diamagnetic) for Nd<sub>2</sub>WO<sub>6</sub> and a positive contribution (paramagnetic) for Gd<sub>2</sub>WO<sub>6</sub>, Dy<sub>2</sub>WO<sub>6</sub> and Ho<sub>2</sub>WO<sub>6</sub>. It also indicated that a temperature independent paramagnetic contribution was favoured by the RE<sub>2</sub>WO<sub>6</sub> compounds with a higher atomic number. However, in all compounds RE<sub>2</sub>WO<sub>6</sub> the Landau, Pauli and van Vleck contributions were present but in different proportions so that different signs appeared as they could not be separated [1].

Doped and undoped rare-earth metal molybdates and tungstates are host candidates for luminescent applications. They are used for a fabrication of white light-emitting diodes showing high stability, energy-saving and safety [2, 3]. Thus, the main purpose of the present work is an attempt to study in more detail magnetic isotherms and correlate them with formation of the sub-micron sized particles or nanoparticles with the stable magnetization vector as the RE<sub>2</sub>WO<sub>6</sub> tungstates under study are the paramagnetic powders.

## 2. Experimental details

The magnetization isotherms were measured in the zero-field-cooled (ZFC) mode and in external magnetic

fields up to 14 T and at 4.2, 10, 15, 20, 30, 40 and 60 K using a step-magnetometer. RE<sub>2</sub>WO<sub>6</sub> (RE = Nd, Sm, Eu, Gd, Dy, Ho and Er) were synthesized by a solid-state reaction between RE<sub>2</sub>O<sub>3</sub> and WO<sub>3</sub> mixed at the molar ratio 1:1. The RE<sub>2</sub>O<sub>3</sub>/WO<sub>3</sub> mixtures were heated in the following cycles: 800 °C (12 h), 900 °C (12 h), 1000 °C (12 h) and 1100 °C (2 × 12 h). A routine phase analysis was conducted using a DRON-3 diffractometer run with Co  $K_\alpha$  radiation ( $\lambda = 0.179021$  nm). Diffraction patterns were collected over 12–60°  $2\theta$  at a stepped scan rate of 0.02° per step and a count time of 1 s per step. For the indexing procedure diffraction patterns were collected using a X'Pert PRO Philips diffractometer at the stepped scan rate of 0.02° per step and a count time of 10 s per step [4].

## 3. Results and discussion

All these tungstates have two features in common: both zero coercivity and remanence. Figure 1 shows spontaneous magnetization without hysteresis loop for Nd<sub>2</sub>WO<sub>6</sub>. With increasing temperature a transition to the ideal paramagnetic state is observed. Figure 2 shows a non-cooperative magnetism for Eu<sub>2</sub>WO<sub>6</sub> arising from spontaneous moments which are identical and located in isotropic surroundings, sufficiently separated to be independent of the others' existence. Similar behaviour was observed for Sm<sub>2</sub>WO<sub>6</sub>, not shown for clarity. Figures 3 and 4 reveal spontaneous magnetization with hysteresis loop for Gd<sub>2</sub>WO<sub>6</sub> and Er<sub>2</sub>WO<sub>6</sub>. Above 60 K a transition to the ideal paramagnetic state is observed. Similar behaviour was also observed for Dy<sub>2</sub>WO<sub>6</sub> and Ho<sub>2</sub>WO<sub>6</sub>, not shown for clarity. The small values of magnetic moment for Sm<sub>2</sub>WO<sub>6</sub> and Eu<sub>2</sub>WO<sub>6</sub> may be connected with the fact that the narrower multiplet widths, comparable




Fig. 1. Magnetic moment  $\mu$  vs. magnetic field  $\mu_0H$  for  $Nd_2WO_6$  at 4.2, 10, 15, 20 and 30 K.




Fig. 2. Magnetic moment  $\mu$  vs. magnetic field  $\mu_0H$  for  $Eu_2WO_6$  at 4.2, 10, 15 and 20 K.

to  $kT$ , occur in the case of samarium and europium [5], so that not all the atoms are in their ground state [6]. Such levels above the ground state may not contribute to the magnetic moment [7].

No hysteresis in the non-linear dependence of  $\mu(\mu_0H)$  and the universal function of  $\mu_0H/T$  [8] (Fig. 5) characterise superparamagnetic-like behaviour for the finely divided  $Nd_2WO_6$  material into sub-micron sized particles with fluctuating magnetization vector among the easy directions of magnetization. In the case of the  $Gd_2WO_6$ ,  $Er_2WO_6$ ,  $Dy_2WO_6$  and  $Ho_2WO_6$  tungstates the hysteresis occurs and the fluctuations of the magnetization vector among the easy directions of magnetization are blocked. In other words, the hysteresis both with zero coercivity and remanence is a consequence of an appearance of the stable magnetization of a single domain particle and the temperature at which this occurs is called




Fig. 3. Magnetic moment  $\mu$  vs. magnetic field  $\mu_0H$  for  $Gd_2WO_6$  at 4.2, 10, 15, 20, 30, 40 and 60 K. A run of magnetic field is indicated by arrows.




Fig. 4. Magnetic moment  $\mu$  vs. magnetic field  $\mu_0H$  for  $Er_2WO_6$  at 4.2, 10, 15, 20 and 30 K. A run of magnetic field is indicated by arrows.

the blocking temperature ( $T_B$ ) [8]. For the tungstates above mentioned  $T_B$  does not exceed 30 K. In our case the blocking temperature may be equivalently defined as the temperature at which the hysteresis loop disappears.

The nature of hysteresis occurring in Figs. 3 and 4 may be connected with the uniaxial anisotropy [9] coming from the spin-orbit coupling driven from the Brillouin fit of the Landé factor [1] and the anisotropy distribution of the electron density. When the system involves magnetic moments with an easy magnetization axis the anisotropy energy reaches minimum. The value of the anisotropy energy defined as 1/8 of the area of the hysteresis cycle, whatever its shape [9] decreases with increasing temperature. The hysteresis width is the largest for the  $Gd_2WO_6$  with the  $f^7$  configuration and slightly decreases when it tends to  $f^{11}$ , i.e. for  $Er_2WO_6$ .




Fig. 5. Magnetic moment  $\mu$  as a function of  $\mu_0 H/T$  for  $\text{Nd}_2\text{WO}_6$  showing superparamagnetic-like behaviour.




Fig. 6. Magnetic moment  $\mu$  as a function of  $\mu_0 H/T$  for  $\text{Eu}_2\text{WO}_6$  showing ideal paramagnetic behaviour.

Figure 6 shows the magnetization curves  $\mu(\mu_0 H/T)$  for the  $\text{Eu}_2\text{WO}_6$  tungstate for that the universal function

of magnetization,  $\mu(\mu_0 H/T)$ , is absent indicating only a paramagnetic state with the strongly reduced magnetic moment.

#### 4. Conclusions

We have measured the magnetization isotherms in the ZFC mode of the powder  $\text{RE}_2\text{WO}_6$  tungstates. The results showed a paramagnetic state for tungstates with samarium and europium and the superparamagnetic-like behaviour with fluctuating magnetization vector for  $\text{Nd}_2\text{WO}_6$  as well as with the blocked magnetization vector for  $\text{Gd}_2\text{WO}_6$  and  $\text{Er}_2\text{WO}_6$  below 30 K. The hysteresis loops with zero remanence and coercivity indicate that the powder tungstates under study seem to be formed as the ferromagnetic single-domain particles not interacting between them.

#### Acknowledgments

This work is partly funded by Ministry of Scientific Research and Information Technology.

#### References

- [1] P. Urbanowicz, E. Tomaszewicz, T. Groń, H. Duda, A.W. Pacyna, T. Mydlarz, *Physica B* **404**, 2213 (2009).
- [2] S. Neeraj, N. Kijima, A.K. Cheetham, *Chem. Phys. Lett.* **387**, 2 (2004).
- [3] T. Kim, S. Kang, *J. Lumin.* **122-123**, 964 (2007).
- [4] E. Tomaszewicz, *Solid State Sci.* **8**, 508 (2006); *Thermochim. Acta* **447**, 69 (2006).
- [5] A. Earnshaw, *Introduction to Magnetochemistry*, Academic Press, London 1968.
- [6] A.H. Morrish, *Physical Principles of Magnetism*, Wiley, New York 1965.
- [7] C. Kittel, *Introduction to Solid State Physics*, Wiley, New York 1960.
- [8] C.M. Hurd, *Contemp. Phys.* **23**, 469 (1982).
- [9] J.J. Prejean, M.J. Joliclerc, P. Mond, *J. Phys.* **41**, 427 (1980).